

1. 성적서 번호 : CMT2019 - 0510 5. 접수일자 : 2018년 10월 31일
 2. 의뢰인 업체명 : 한일시멘트(주) 6. 발급일자 : 2019년 01월 24일
 주소 : 서울특별시 강남구 강남대로 330(역삼동)
 성명 : 한일시멘트(주) 대표이사 곽의영
 3. 성과이용목적 : 품질관리 및 공급원승인용
 4. 시료명 : 레미픽스 13000 TYPE III

시험 결과

연번	시험 · 검사종목		단위	시험 · 검사방법	시험 · 검사결과
1	접착 강도	표준	N/mm ²	KS L 1593 : 2016	1.1
		건조·습윤	N/mm ²		0.9
		열노화	N/mm ²		0.8
		저온·경화	N/mm ²		0.7
2	내열성		-	이상 없음	
3	미끄럼 저항성		-	이상 없음	
4	부착 가능 시간		분	30	

담당자 : 문승권

문승권

기술책임자 : 신도철

Tel : 031-646-0811

Tel : 031-646-0801

SKM

- ※ 비고 : 1. 이 시험성적서는 당초 의뢰자가 제출한 시료 및 시료명으로 시험한 결과로서 전체 제품에 대한 품질을 보증 하지는 않습니다.
 2. 이 성적서는 홍보, 선전, 광고 및 소송용으로 사용될 수 없으며, 용도 이외의 사용을 금합니다.
 3. 이 성적서의 원본 진위확인은 한국에스지에스 온라인 성적서 조회 홈페이지(<http://e-checking.kr.sgs.com/construction/>)에서 열람이 가능합니다.

한국에스지에스(주) 건설시험협회원



주 소 : 경기도 화성시 동탄면 동탄산단10길 20 전화번호 (031)669-0600

유의사항 : 기술책임자의 성명과 서명이 없는 경우에는 결과에 대한 보증을 할 수 없습니다.

페이지 1 / 1

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

KOR2019-001-F07 (07)

SGS Korea Co., Ltd.

20, Dongtansandan 10-gil, Dongtan-myeon, Hwaseong-si, Gyeonggi-do, Korea, 18487 t +82(0)31 646 0600 f +82(0)31 646 0888 www.sgs.com

Member of SGS Group(Société Générale de Surveillance)



한국에스지에스(주) 건설시험연구원

성적서 번호

: CMT2020-0570

주소: 경기도 화성시 동탄면 동탄산단10길 20
 전화: 031-669-0600 팩스: 031-646-0888
<https://www.sgsgroup.kr>

1. 의뢰인

- 기관명 : 한일시멘트(주)
- 주소 : 서울특별시 강남구 강남대로 330
- 의뢰일자 : 2019년 11월 04일

2. 시험성적서의 용도 : 품질관리 및 공급원승인용

3. 시험대상품목 또는 물질, 시료명 : 레미픽스 17000W - TYPEII

4. 시험기간 : 2019년 11월 11일 ~ 2019년 12월 31일

5. 시험장소 : ■ 고정시험실 □ 현장시험

(주소: 경기도 화성시 동탄면 동탄산단 10길 20, 한국에스지에스(주) 콘크리트/모르타르 시험실)

6. 시험결과 :

연번	시험종목	단위	시험방법	시험결과
1	접착 강도	표준	KS L 1593 : 2016	1.4
		건조·수중		0.7
		열노화		1.2
		저온 경화		1.3
		알칼리 수중		0.6
2	내열성	-		이상 없음
3	미끄럼 저항성	-		이상 없음
4	가사시간	시간		25
5	부착 가능 시간	시간		12

-끝-

실무자 : 문승권

Tel : 031-646-0811

기술책임자 : 김동훈

Tel : 031-646-0812

※ 비고 : 1. 이 시험성적서는 당초 의뢰자가 제출한 시료 및 시료명으로 시험한 결과로서 전체 제품에 대한 품질을 보증 하지는 않습니다.
 2. 이 성적서는 홍보, 선전, 광고 및 소송용으로 사용될 수 없으며, 용도 이외의 사용을 금합니다.
 3. 이 성적서의 원본 진위확인은 한국에스지에스 온라인 성적서 조회 홈페이지(<http://e-checking.kr.sgs.com/construction/>)에서
 열람이 가능합니다.

2020년 01월 22일

한국에스지에스(주) 건설시험연구원

페이지 1 / 1

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

COP-708-001-F08 (01)

SGS Korea Co.,Ltd. 20, Dongtansandan 10-gil, Dongtan-myeon, Hwaseong-si, Gyeonggi-do, Korea, 18487 t +82(0)31 669 0800 f +82(0)31 669 0888 www.sgs.com

Member of SGS Group(Société Générale de Surveillance)



한국에스지에스(주) 건설시험연구원

성적서 번호 : G-21-0411-R0
진위확인용 랜덤번호 : SGSv3oq4nN

주소: 경기도 화성시 동탄면 동탄산단10길 20

전화: 031-669-0600 팩스: 031-646-0888

<https://www.sgsgroup.kr>

1. 의뢰인

- 기관명 : 한일시멘트(주)
- 주소 : 서울특별시 서초구 서초동 1587
- 의뢰일자 : 2020년 10월 30일

2. 시험성적서의 용도 : 품질관리 및 공급원승인용

3. 시험대상품목 또는 물질, 시료명 : 레미픽스 17000 – TYPE III

4. 시험기간 : 2020년 10월 30일 ~ 2021년 01월 20일

5. 시험장소 : ■ 고정시험실 □ 현장시험

(주소: 경기도 화성시 동탄면 동탄산단10길 20, 한국에스지에스(주) 콘크리트/모르타르 시험실)

6. 시험결과 :

연번	시험종목	단위	시험방법	시험결과
1	접착 강도	표준	KS L 1593 : 2020	1.6
		건조 습윤		1.5
		열노화		1.3
		저온 경화		1.2
2	내열성	-		이상 없음
3	미끄럼 저항성	-		이상 없음
4	부착 가능 시간	분		50

-끝-

실무자 : 문승권

문승권

Tel : 031-646-0811

기술책임자 : 김호진

김호진

Tel : 031-646-0804

- ※비고 :
1. 이 시험성적서는 당초 의뢰자가 제출한 시료 및 시료명으로 시험한 결과로서 전체 제품에 대한 품질을 보증 하지는 않습니다.
 2. 이 성적서는 홍보, 선전, 광고 및 소송용으로 사용될 수 있으며, 용도 이외의 사용을 금합니다.
 3. 이 성적서의 원본 진위확인은 한국에스지에스 온라인 성적서 조회 홈페이지(<http://e-checking.kr.sgs.com/construction/>)에서 열람이 가능합니다.(랜덤 번호 기재 요)

2021년 01월 28일



한국에스지에스(주) 건설시험연구원

페이지 1 / 1

This document is issued by the Company under its General Conditions of Service accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

CQP-708-001-F08 (01)